

## RonaBond Bedding Mortar

### Pre-packed mortar for bedding brick slips and building components



#### FEATURES

- pre-packed brick slip bedding mortar
- British Board of Agrément approved for bedding brick slips
- waterproof and frostproof
- excellent durability
- monolithic adhesion
- high strength and waterproof

#### Description

RonaBond Bedding Mortar is used to bond brick slips, copings and other components to concrete and building surfaces. The cured mortar has high physical strength, is waterproof and frost proof and will not break down through frost action.

Ronacrete Standard Primer is used to provide monolithic adhesion between the mortar, the slip and the substrate. Careful surface preparation is essential to ensure adhesion, long term durability and performance.

#### Performance Data

##### Freeze / thaw cycle tests

Temperature Range	-18°C/+20°C
Flexural Strength Initial	11.6N/mm <sup>2</sup>
Flexural Strength After 120 Cycles	11.0N/mm <sup>2</sup>

##### Pull off tests—Calcium Silicate Brick

Normal Cure	1.05N/mm <sup>2</sup>
Immersed in CaCO <sub>3</sub>	0.50N/mm <sup>2</sup>
Freeze / Thaw (50 cycles)	0.71N/mm <sup>2</sup>
Thermal Cycling	0.81N/mm <sup>2</sup>

##### Pull off tests—Clay Bricks

Normal Cure	1.55N/mm <sup>2</sup>
Immersed in CaCO <sub>3</sub>	1.07N/mm <sup>2</sup>
Freeze / Thaw (50 cycles)	1.03N/mm <sup>2</sup>
Thermal Cycling	1.28N/mm <sup>2</sup>

**In no case did the brick / mortar or concrete / mortar bond fail.**



# RonaBond Bedding Mortar

## Pre-packed mortar for bedding brick slips and building components

### Performance Data (continued)

#### Compressive Strength

1 day	22N/mm <sup>2</sup>
3 days	34N/mm <sup>2</sup>
7 days	42N/mm <sup>2</sup>
28 days	53N/mm <sup>2</sup>

#### Tensile Strength

7 days	5.7N/mm <sup>2</sup>
28 days	8.4N/mm <sup>2</sup>

#### Flexural Strength

7 days	15.8N/mm <sup>2</sup>
28 days	19.1N/mm <sup>2</sup>

### Physical Properties

Pack Size	25kg
Packs required per m <sup>3</sup>	91 packs
Yield per pack	11 litres
Coverage per pack	1m <sup>2</sup> @ 11mm
Min / max application depth	6mm / 10mm

### Coverage

One 25kg pack of RonaBond Bedding Mortar will fix 70 slips (65mm x 225mm) using a 10mm bed. One 2kg pack of Ronacrete Standard Primer is sufficient for 150 slips (concrete surface and slip).

### Instructions for Use

1. The surface to receive the slip must be mechanically prepared to ensure it is structurally sound and stable and strong enough to support the weight of the slip and the mortar.
2. The surface must be mechanically abraded by scabbling, needle gunning or similar methods to provide a strong, laitence free profile. Any coatings must be removed back to clean, sound concrete. Clean the surface to remove dust and debris.
3. The back of the brick slip / component must be cleaned to remove loose material and any contamination.
4. Damp the surface and the back of the slip / component with clean water; remove excess water.
5. Apply a single coat of Ronacrete Standard Primer to the damp surfaces; the primer must remain wet or tacky and must not dry before the mortar is applied.
6. Mix RonaBond Bedding Mortar as described (see Mixing).
7. Trowel the mortar on to the back of the slip / component, or on to the surface, to a bed depth of 6-12mm (typically).
8. Place the slip / component in to the mortar, position and brace. Ensure total contact between the slip / component, mortar and concrete.
9. Support the slip as necessary until the mortar has hardened sufficiently.
10. Avoid staining the face of slip with the primer or mortar.



# RonaBond Bedding Mortar

## Pre-packed mortar for bedding brick slips and building components

### Instructions for Use (continued)

#### Mixing

RonaBond Bedding Mortar provides optimum performance when machine mixed in a forced action mixer (eg. Creteangle pan mixer). Do not use a free fall mixer. Mix the dry components and when evenly dispersed add the minimum amount of the supplied gauging liquid to provide sufficient workability for compaction and surface finish.

### Application Temperature

RonaBond Bedding Mortar can be used in most weather conditions and in a wide temperature range, typically from +3°C to 25°C and above. Note that at high ambient temperatures the working time of the mix will be reduced; it will be increased at lower temperatures. Ideally store materials between 10°C and 20°C before use.

### Technical and Test Data

Note that all quoted data is based on laboratory tests conducted at 20°C. Cubes, tested at 28 days, are 100mm and air cured. Results shown are MAXIMUM laboratory strengths achieved by casting and curing cubes in ideal working conditions; site strengths will be lower.

### Shelf Life and Storage

RonaBond Bedding Mortar should be stored unopened between 5°C and 25°C in dry warehouse conditions and out of direct sunlight. In these conditions shelf life is approximately 9 months.

### Health and Safety

RonaBond Bedding Mortar is non-hazardous although protective clothing such as goggles, overalls and gloves is recommended to prevent any effect from prolonged skin contact, inhalation or ingestion.

In the event of skin contact, wash with soap and water. Seek medical advice if irritation or pain occurs. In the event of eye contact, irrigate with plenty of clean water and seek immediate medical advice. In the event of ingestion, do not induce vomiting. Seek immediate medical advice.

### Site Attendance

When on site Ronacrete representatives are able, if asked, to give a general indication of the correct method of installing a Ronacrete product. It is important to bear in mind that Ronacrete Ltd is a manufacturer and not an application contractor and it is therefore the responsibility of the contractor and his employer to ensure he is aware of and implements the correct practices and procedures to ensure the correct installation of the product and that liability for its correct installation lies with the contractor and not with Ronacrete Ltd.



# RonaBond Bedding Mortar

Pre-packed mortar for bedding brick slips and building components

Ronacrete Ltd, Flex Meadow, Harlow Essex, CM19 5TD, UK  13 0836-CPR-13/F044
BS EN 988-2  Masonry Mortar
<b>Product: RonaBond Bedding</b> <b>Compressive Strength at 28 days at 20C: &gt; 45N/mm<sup>2</sup></b> <b>Content of Chlorides : &lt; 0.1%</b> <b>Reaction to Fire: A2-s1,d0</b> <b>Capillary Water Absorption: W1 &lt; 0.40kg /m<sup>2</sup> . min0.5</b> <b>Dangerous Substances : Refer to Safety Data Sheet</b>

The information detailed in this leaflet is liable to modification from time to time in the light of experience and of normal product application, and before using, customers are advised to check with Ronacrete Ltd, quoting the reference number, that they possess the latest issue. Any person or company using the product without first making further enquiries as to the suitability of the product for the intended use does so at his own risk, and Ronacrete Ltd can accept no responsibility for the performance of the product, or for any loss or damage arising out of such use.