

## RonaBond Concrete Cover 150

Coating to increase equivalent concrete cover by up to 150mm



### FEATURES

- protective coating for concrete
- 4mm application increases Equivalent Concrete Cover by 150mm
- waterproof
- easy to apply

### Description

RonaBond Concrete Cover 150 is a coating designed to improve equivalent concrete cover to reinforcement. A 4mm layer provides 150mm equivalent concrete cover providing corrosion protection to steel reinforcement thus extending the life of the concrete.

RonaBond Concrete Cover 150 is supplied as a pre-packed material comprising liquid and powder. It is mixed to form a slurry which is applied by brush or roller at a thickness of approximately 0.5mm per coat on a vertical surface. The cured coating can be left as the finished surface or overcoated with a pigmented anti-carbonation coating such as RonaBond Crack Bridging Anti-Carbonation Coating WB or RonaBond Anti-Carbonation Coating WB.

Independent laboratory testing demonstrates that 4mm of RonaBond Concrete Cover 150 provides 150mm equivalent concrete cover. **Please note that RonaBond Concrete Cover 150 is for corrosion protection and will not improve the fire rating of concrete with insufficient cover.**

### Physical Properties

Coverage (approximately)

To apply a 4mm coating over 1m<sup>2</sup> requires approximately 7.2kg of RonaBond Concrete Cover 150  
Dark Grey

Cured colour

Waterproof ISAT Value (ml/m<sup>2</sup>/sec)

0.00

Adhesion

Monolithic

No of coats

Up to 8 depending on orientation and required improvement to cover.

### Test Data

Oxygen Diffusion DO<sub>2</sub> (cm<sup>2</sup>/s)\*

7.39 x 10<sup>-5</sup>

Carbon Dioxide Diffusion Coefficient

DCO<sub>2</sub> (cm<sup>2</sup>/s)\*

2.21 x 10<sup>-5</sup>

Equivalent Concrete Thickness Sc (cm)\*

15

## RonaBond Concrete Cover 150

Coating to increase equivalent concrete cover by up to 150mm

### Instructions for Use

#### Preparation

The substrate on which RonaBond Concrete Cover 150 is being placed must be structurally sound and stable. Surfaces should ideally be prepared by water/grit blasting or similar means to remove previous coatings and any grease, oil, dirt and deleterious material. Damp the surface with clean water and remove excess.

#### Mixing

Mix RonaBond Concrete Cover 150 with a slow speed drill and helical paddle. .

Dry mix the powder to ensure the fine and coarse particles are thoroughly blended.

Slowly add all of the supplied liquid and continue mixing until the components are fully blended; reducing the gauging liquid content will reduce the effectiveness of the coating. RonaBond Concrete Cover 150 is supplied pre-packed and no on site additions are required.

#### Application

As soon as the material is mixed apply by brush or roller to the damp surface ensuring total coverage and a uniform surface appearance.

Apply the first coat and allow to dry for approximately 12-24 hours at 20°C.

Mix and apply successive coats at 90° to the previous coats and allow each to dry for approximately 12-24 hours at 20°C.

### Packaging and Coverage

RonaBond Concrete Cover 150 is supplied as a two pack material in 19kg packs. One pack of material is sufficient to apply one coat over an area of approximately 21m<sup>2</sup> at a thickness of 0.5mm.

### Health and Safety

Refer to Safety Data Sheet.


### Site Attendance

When on site Ronacrete representatives are able, if asked, to give a general indication of the correct method of installing a Ronacrete product. It is important to bear in mind that Ronacrete Ltd is a manufacturer and not an application contractor and it is therefore the responsibility of the contractor and his employer to ensure he is aware of and implements the correct practices and procedures to ensure the correct installation of the product and that liability for its correct installation lies with the contractor and not with Ronacrete Ltd.



## RonaBond Concrete Cover 150

Coating to increase equivalent concrete cover by up to 150mm

 <b>0836</b>
Ronacrete Ltd, Flex Meadow, Harlow Essex, CM19 5TD, UK  <b>13</b> <b>0836-CPR-13/F045</b>
<b>BS EN 1504-2</b>  <b>Concrete Repair Surface Protection System</b>
<b>Product: RonaBond Concrete Cover 150</b> <b>Capillary abs. &amp; perm. to water: <math>W &lt; 0.1\text{kg/m}^2 \cdot \text{h}0.5</math></b> <b>Reaction to Fire: Euroclass F</b> <b>Dangerous Substances: Refer to Safety Data Sheet</b>

The information detailed in this leaflet is liable to modification from time to time in the light of experience and of normal product application, and before using, customers are advised to check with Ronacrete Ltd, quoting the reference number, that they possess the latest issue. Any person or company using the product without first making further enquiries as to the suitability of the product for the intended use does so at his own risk, and Ronacrete Ltd can accept no responsibility for the performance of the product, or for any loss or damage arising out of such use.